

**Mostra 11: Finisaj epoxidic Design Granit**

- Clasa de reactie la foc: Bfl

**Consumuri:****1. Strat de grund:**

- Rasina epoxidica GH 50: cca. 300 g/m<sup>2</sup>

**2. Presarare nisip:**

- Nisip de quart QS 98 sort 0,3 – 0,8 mm: cca. 1,5 kg/m<sup>2</sup>

**3. Mortar epoxidic autonivelant:**

- Rasina epoxidica EP 70 BM: cca. 600 g/m<sup>2</sup>
- Nisip de quart QS 98 sort 0,1 – 0,2 mm: cca. 600 g/m<sup>2</sup>
- Nisip de quart QS 98 sort 0,3 – 0,8 mm: cca. 600 g/m<sup>2</sup>

**4. Finisaj epoxidic Design Granit:**

- Rasina epoxidica EP 220: cca. 1,2 kg/m<sup>2</sup>
- Adaos granular pt. covoare Design: cca. 2 kg/m<sup>2</sup>