

Mostra 11: Finisaj epoxidic Design Metalic

- Clasa de reactie la foc: Bfl

**Consumuri:****1. Strat de grund:**

- Rasina epoxidica GH 50: cca. 300 g/m²

2. Presarare nisip:

- Nisip de quart QS 98 sort 0,3 – 0,8 mm: cca. 1,5 kg/m²

3. Mortar epoxidic autonivelant:

- Rasina epoxidica GH 50: cca. 600 g/m²
- Nisip de quart QS 98 sort 0,1 – 0,2 mm: cca. 600 g/m²
- Nisip de quart QS 98 sort 0,3 – 0,8 mm: cca. 600 g/m²

4. Finisaj epoxidic Design Granit:

- Rasina epoxidica EP 220: cca. 2 kg/m²
- Adaos metalic pt. covoare Design: cca. 20 g/m²