


Mostra 5: Finisaj epoxidic EP 2 neted

- Clasa de reactie la foc: Bfl



Consumuri:

1. Strat de grund:

- Rasina epoxidica EP 70 BM: cca. 300 g/m²

2. Presarare nisip:

- Nisip de quart QS 98 sort 0,3 – 0,8 mm: cca. 1,5 kg/m²

3. Mortar epoxidic autonivelant:

- Rasina epoxidica EP 70 BM: cca. 600 g/m²
- Nisip de quart QS 98 sort 0,1 – 0,2 mm: cca. 600 g/m²
- Nisip de quart QS 98 sort 0,3 – 0,8 mm: cca. 600 g/m²

4. Finisaj epoxidic in amestec cu nisip de quart:

- Finisaj epoxidic EP 2 RAL 7044: cca. 2 kg/m²
- Nisip de quart QS 98 sort 0,1 – 0,2 mm: cca. 800 g/m²

